

# Technical Data Sheet

Product Name	
Full Product Name	<b>701 2K Metal Clear (4:1)</b>
Type of Product	2K Acrylic Urethane Clearcoat
Description	Concept 701 2K Metal Clear (4:1) is a high gloss 2K clearcoat, designed for use over all metals. It can be used directly over aluminium and stainless steel. It is characterized by excellent flow, producing a high gloss with very good chemical resistance, hardness and durability.

Products						
Product Name	Volume Solids %	Weight Solids %	Density		VOC	
			g/mL	lbs/US gal	g/L	lbs/US gal
701 2K Metal Clear (4:1)	35.3	39.7	0.976	8.15	589.2	4.92
241 PU Hardener (4:1) Slow	35.4	40.9	1.004	8.38	593.8	4.96
241 PU Hardener (4:1) Normal	33.9	39.9	0.986	8.23	593.1	4.95
241 PU Hardener (4:1) Fast	33.6	40.2	0.968	8.08	578.3	4.83
831 2K Thinner Slow	0.0	0.0	0.893	7.45	892.7	7.45
831 2K Thinner Normal	0.0	0.0	0.882	7.36	881.9	7.36
831 2K Thinner Fast	0.0	0.0	0.872	7.27	871.5	7.27

Properties
<ul style="list-style-type: none"> <li>Suitable for Direct-To-Metal (DTM) Application as well as suitable over all CONCEPT range of basecoat systems.</li> <li>Fast drying</li> <li>Excellent through cure</li> <li>Excellent levelling and flow</li> <li>Excellent chemical resistance and durability</li> </ul>

# Technical Data Sheet

## Substrates

- Concept No Mix system colours
- Concept No Mix-e Basecoat System colours
- Concept Unicolour 900 2K Basecoat system colours
- Mild Steel, Stainless Steel, Aluminium, Brass and other paintable non-ferrous alloys

## Substrate Preparation












### All Substrates

All Metal surfaces must be cleaned with Concept Ant-Static Cleaner and free from any contamination prior to application.

# Technical Data Sheet

## Product Preparation

	<b>Mixing Ratio</b> 4:1 (by volume)			<b>Concept 701</b> <b>2K Metal Clear (4:1)</b>	<b>Concept</b> <b>241 PU Hardener</b>
				4 parts	1 part
	<b>Reducer</b>	Up to 5% (v/v) of 831 2K Thinner Normal, if required.			
	<b>Pot life</b> @ 25°C (77°F)	6-8 hours			
	<b>Spray viscosity</b> @ 25°C (77°F)	<b>BSB 4 Cup</b> <b>Ford 4 Cup</b>	17-18 s 15-16 s		
	<b>Spray equipment</b>	<b>Gun type</b>	<b>Fluid tip</b>	<b>Spray pressure</b>	<b>Spray Distance</b>
		<b>Gravity feed</b>	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		<b>Suction feed</b>	1.3-1.4 mm 0.051-0.055"	200-240 kPa 2.0-2.4 bar 30-35 psi	15-20 cm 6-8 inch
		<b>HVLP</b>	1.2-1.3 mm 0.047-0.051"	40-70 kPa 0.4-0.7 bar 6-10 psi	15-20 cm 6-8 inch
	<b>Number of coats</b>	2	Apply two even full coats. Avoid heavy wet coats.		
	<b>DFT</b> Recommended	40-50 µm 1.6-2.0 mils			
	<b>Flash off time</b> @ 25°C (77°F)	10-15 min between coats			
	<b>Drying</b>	<b>Air Dry</b> @ 25°C (77°F)	Overnight		
		<b>Low Bake</b> @ 50°C (122°F)	30 min		

This data relates only to the material designated herein and does not apply to use in combination with any other material or any process. The data is not to be considered as a warranty or quality specification and we assume no liability in connection with its use.

# Technical Data Sheet

## Remarks



Stir all products thoroughly each time before use.  
Stir the mixture well after the weigh-out of the components.



Surface temperature must always be a minimum of 3°C  
(5°F) above dew point.

## Equipment Cleaning

Use recommended Concept Paints 035 Gunwash

## Dry Film Properties

After 7 days drying,  
**when compared to similar technology products.**

Gloss

High

Hardness

Excellent

Chemical resistance

Excellent

Durability

Excellent

## Product Data

Colour

Water white

Theoretical Coverage

Approx. 6.0 m<sup>2</sup>/L (245 ft<sup>2</sup>/US gal) @ recommended DFT

Shelf Life

36 months in an unopened container at room  
temperature, away from sunlight.

# Technical Data Sheet

## Product Packaging

Product Code	Product Name	Package Size
IN7019000000X	701 2K Metal Clear (4:1)	1L, 4L
IN2419100000X	241 PU Hardener (4:1) Slow	250mL, 1L
IN2419200000X	241 PU Hardener (4:1) Normal	250mL, 1L
IN2419300000X	241 PU Hardener (4:1) Fast	250mL, 1L
IN83191000020	831 2K Thinner Slow	20L
IN83192000020	831 2K Thinner Normal	20L
IN83193000020	831 2K Thinner Fast	20L

## Safety

For automotive and industrial use only by professional painters. Not recommended for sale to, or use by the general public. Before using, read and follow all label and Safety Data Sheet (SDS) precautions. If mixed with other components, the mixture will have hazards of all individual components.

Read and understand the Guidelines for the Safe Handling and Use of Isocyanate Containing Paints, including the use of approved respiratory protection and Personal Protective Equipment. Use only in a well-ventilated approved spray booth, according to local regulations.

The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check if the information is current and the product is suitable for its intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved.

We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

This Technical Data Sheet supersedes all previous issues.

Concept Paints  
26-30 Charles Street  
St Marys NSW 2760  
Sydney, Australia

ph. +61 (2) 9673 2555  
fax. +61 (2) 9623 1918  
office@conceptpaints.com.au  
www.conceptpaints.com.au

# Technical Data Sheet